



SPRAY P 962 1K ISOLATOR PRIMER

Technical Data Sheet No 830



VOC compliant with the regulations.

One component air drying system

Dries quickly

P 962 1K ISOLATOR PRIMER prevents lifting and bleeding of existing old paint films, sensitive to strong solvents.

General Technical Description

2 passes

Surface

All metallic and wooden surfaces

Adhesion to any coated surface

Pretreatment / Cleaning of substrate



Clean substrate using a soft cloth and BODY 770 ANTISIL NORMAL/ BODY 771 ANTISIL FAST

Use P 400 for wet sanding, re-clean the surface and dry thoroughly

Use P 180 for sanding on applications direct to metals



Make sure you always use appropriate face protection and good ventilation

Product Application: >>> Apply on a light sanded surface using wet / dry P180 grit paper. Apply 2 light coats at an approximately distance of 20 - 25cm. No sanding after application.



Shake well before using

Flash Point:
-97°C

Remarks:

- Always try to use the product in accordance with the specifications provided.
- It can be used by countries that do not adopt the VOC legislation as well.
- Shake thoroughly before use.
- Shake for 1-2 mins after agitator ball has started to rattle. After preparing the area to be painted ensure it to be free from dirt, wax, oil etc. Test on a similar surface using a back and forth action.
- Spray at a distance of 25 cm thinly applied coats build up at 3-5 minutes intervals will achieve best results.
- Optimum operating temperature range 10-25°C.

Storage shelf life:

- Store in a cool place (+5°C - +25°C) and use within 12 months for best results. Guaranteed shelf life of 24 months in unused original containers.
- Do not overload



2 coats approximately 20 - 25microns

Specific Gravity:
0,95 g/cm³

Solid Content (No thinner):
35% Weight

VOC (2004/42/EC)

This product is an aerosol product based on its ingredients and its properties. The maximum VOC content in this category is 840 g/L. The VOC content in the ready for use form of this product is 585g/L. 2004/42/IIIB(e)(840)585

Theoretical Coverage:
-

Cleaning of equipment:
-



Dust free 10 - 15min at 23°C



Full hardness within 1 hour



Overcoat with primer / surfacer